Docket No.: 0630-1835P

## **AMENDMENTS TO THE CLAIMS**

1. (Currently Amended) A method for forming a pattern, comprising:

providing a substrate on which a plurality of unit panels and etching object layers on the respective unit panel areas are formed;

dividing the substrate into at least two areas, each of the two areas having at least one unit panel;

providing a cliché on which a plurality of grooves are formed, the cliché being divided into a plurality of areas corresponding to the divided areas of the substrate;

filling resist in the grooves;

transferring the resist in the grooves of one area of the cliché on a blanket applied on a surface of a printing roll by contacting and rotating the printing roll with the blanket on the cliché, the printing roll corresponding to the divided area of the substrate; and

applying the resist transferred on the surface of the blanket on the etching object layer on the area of the substrate corresponding to the area of the cliché.

2. (Previously Presented) The method of claim 1, wherein the printing roll has a same width as that of the divided area of the substrate.

3. (Canceled)

Docket No.: 0630-1835P

4. (Previously Presented) The method of claim 2, wherein a length of the blanket is the

same as a length of a circumference of the printing roll, which is same as a length of the divided

area of the substrate.

5. (Original) The method of claim 1, wherein the divided area of the substrate includes

one or more unit panels.

6. (Original) The method of claim 1, wherein the cliché is formed to have a same size as

that of the divided area of the substrate.

7. (Original) The method of claim 1, wherein the printing roll is formed to have a same

size as that of the divided area on the substrate.

8. (Original) The method of claim 1, wherein the etching object layer includes a metal

layer.

9. (Original) The method of claim 1, wherein the etching object layer includes an

insulating layer comprised of SiOx or SiNx.

10. (Original) The method of claim 1, wherein the etching object layer is a semiconductor

layer.

11. (Currently Amended) A method for forming a pattern, comprising:

providing a substrate on which a plurality of unit panels and etching object layers on the respective unit panel areas are formed;

dividing the substrate into a plurality of divided areas so as to include at least one or more unit panels;

providing a cliché on which a plurality of grooves are formed, the cliché being divided into a plurality of areas corresponding to the divided areas of the substrate;

filling resist in the grooves of the cliché;

providing a blanket on a printing roll having a same width as that of the divided area of the substrate;

transferring the resist filled in the grooves of the divided area of the cliché onto a surface of the blanket on the printing roll by contacting and rotating the printing roll with the blanket on the divided area of the cliché corresponding to the divided area of the substrate; and

applying the resist transferred on the surface of the blanket on the etching object layer on the area of the substrate corresponding to the divided area of the cliché.

- 12. (Previously Presented) The method of claim 11, wherein applying the resist on the etching object layer is performed by contacting the resist transferred on the surface of the blanket on the printing roll on the substrate and by rotating the printing roll with the blanket.
- 13. (Original) The method of claim 11, wherein the divided area of the substrate includes at least one unit panel.

- Docket No.: 0630-1835P
- 14. (Original) The method of claim 11, wherein the etching object layer includes a metal layer.
- 15. (Original) The method of claim 11, wherein the etching object layer comprises an insulating layer comprised of SiOx or SiNx.
- 16. (Original) The method of claim 11, wherein the etching object layer is a semiconductor layer.
  - 17. (Canceled)
  - 18. (Canceled)
- 19. (Currently Amended) A method for forming a resist pattern on a panel unit, comprising:

transferring a resist material from one or more grooves of a cliché onto a blanket; and transferring the resist material from the blanket onto a surface of an etching object layer on a part of a substrate including the panel unit to form the resist pattern in the panel unit.

20. (Previously Presented) The method of claim 19, wherein the step of transferring the resist material from the one or more grooves of the cliché onto the blanket comprises:

applying the blanket onto a surface of a printing roll; and

rolling the printing roll with the blanket on the cliché.

21. (Previously Presented) The method of claim 20, wherein the step of transferring the resist material from the blanket onto the surface of the etching object layer to form the resist pattern comprises:

rolling the printing roll with the blanket with the resist material thereon on the surface of the etching object layer.

- 22. (Previously Presented) The method of claim 20, wherein size and shape of the blanket, size and shape of the cliché, and size and shape of a surface area of the printing roll are all substantially the same.
  - 23. (Previously Presented) The method of claim 22, wherein the printing roll is cylindrical,
  - a height of the printing roll is substantially equal to a height of the blanket, and a circumference of the printing roll is substantially equal to a length of the blanket.
  - 24. (Previously Presented) The method of claim 22, wherein

the object layer is divided into a plurality of divided areas, and

the size and shape of the blanket is substantially the same as a size and shape of a sum of one or more divided areas of the plurality of divided areas.

Docket No.: 0630-1835P

25. (Previously Presented) The method of claim 24, wherein size and shape of each

divided area of the object layer is substantially the same in size and shape as each of the other

divided areas.

26. (Previously Presented) The method of claim 24, wherein the area of the blanket is less

than an area of the etching object layer.

27. (Previously Presented) The method of claim 26, wherein the area of the etching object

layer is substantially a whole multiple of the area the blanket.

28. (Previously Presented) The method of claim 1, wherein the blanket improves

adhesive force with the resist.

29. (Previously Presented) The method of claim 11, wherein the blanket improves

adhesive force with the resist.

30. (Canceled)

31. (Canceled)

32. (Previously Presented) The method of claim 19, wherein the blanket improves

adhesive force with the resist.